

PRODUCT SPECIFICATION AND TYPICAL RESULT

CUP GREASE No.3 (DG-503)

| Test | Method | Specification | Typical Result |
|---|--|---|--|
| NLGI Grade Thickener Type Texture Color Penetration at 25 °C (Worked 60-Strokes), mm Penetration at 25 °C (Un Worked), mm Dropping Point , °C Water Washout at 79 °C, % washout Base Oil Viscosity Kinematics at 100 °C, cSt. | - Visual ASTM D 217 ASTM D 217 ASTM D 2265 ASTM D1264 ASTM D 445 | 3 Calcium Smooth & Tacky Dark Red 265-295 Report Min.90 Max.10 15 -18 | 3 Calcium Smooth & Tacky Dark Red 275 272 108 2.01 17.45 |

