

**PRODUCT SPECIFICATION**  
**DAIKYO SHOCK ABSORBER OIL 32 (ISO 32)**

Test	Method	Limit	Result
Appearance	Visual	Bright & Clear	Bright & Clear
ISO Viscosity Grade	-	32	32
Color	ASTM D 6045	Report	L0.5(0.4)
Viscosity, Kinematics at 40°C, cSt.	ASTM D 445	28.0-36.0	32.84
Viscosity, Kinematics at 100°C, cSt.	ASTM D 445	Report	5.589
Viscosity Index	ASTM D 2270	Min.95	108
Pour point, °C	ASTM D 5950	Max.-6	-6
Foaming Characteristics, ml			
Sequence I	ASTM D 892	Max.70/0	10/0
Sequence II	ASTM D 892	Max.70/0	20/0
Sequence III	ASTM D 892	Max.70/0	10/0
Density at 30 °C, g/cm <sup>3</sup>	ASTM D 4052	Report	0.8624