

**PRODUCT SPECIFICATION AND TYPICAL RESULT
MP GREASE L-3 (DG-603)**

Test	Method	Specification	Typical Result
NLGI Grade	-	3	3
Thickener Type	-	Lithium	Lithium
Texture	-	Smooth	Smooth
Color	Visual	Yellow	Yellow
Penetration at 25 °C (Worked 60-Strokes), mm	ASTM D 217	220-250	237
Penetration at 25 °C (Un Worked), mm	ASTM D 217	Report	235
Dropping Point , °C	ASTM D 2265	Min.180	208
Copper Strip corrosion, 24 hr at 100 °C, Rating	ASTM D 4048	Max.2B	1a
Oil Separation at 100 °C , 30hr, %wt	ASTM D 6148	Max.5	1.86
Water Washout at 79 °C, % wash out	ASTM D1264	Max.10	2.01
Base Oil Viscosity Kinematics at 40 °C, cSt.	ASTM D 445	170 - 200	178.5

